



## Ottone speciale - JIS H 2202:2016

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
JIS H 2202:2016	CACIN301	min	55	-	-	0.5	0.5	-	0.1	-	-	-	20	-	-	-	-	-	-	-	-
		max	60	0.4	1	1.5	1.5	1	1.5	-	-	0.1	50	-	-	-	-	-	-	-	-